



This website uses cookies to improve the user's experience during working with our network and to provide users with dedicated services and functions. By further use you agree with that.OKDetails

Qinghua Refractories Co.,Ltd Qinghuali Panlong Street 115100 Dashiqiao City	
中国(中华人民共和国)	
	Qinghua Refractories Co.,Ltd Qinghuali Panlong Street 115100 Dashiqiao City 中国(中华人民共和国)

产品/机械

Recommendations for Regenerator of Glass Tank:

(The recommendations aim to give you a general idea of our bricks. The actual application shall be based on specific condition of the glass tank.)

Top Layers

The uppermost 2 to 4 checker layers are confronted with highest temperature, attacked by batch dust and vanadiumoxide from heavy oil, and suffering strong chemical erosion. QMZR-12, a high temperature Magnesia-zirconia brick, with characters of Low A.P., high B.D and good corrosion resistance, is recommended.

Hot zone:

Suffering severe stress by high temperature, Fused Magnesia bricks (QDMZ-98 or QDMZ-97) are recommended for this area, with proven good performance and not easily cracking or spalling.

Intermediate zone:

This area has less dust erosion, but more strict attack of sulfate penetration, which requires strong resistances to high temperature and thermal shock.

Recommendations: High quality Magnesite bricks (QDMZ-96, QMZ-97 or QMZ-95)

Lower zone:

This zone has lower flue gas temperature, but seriously affected by volatile components and complex sulfate condensation (alkali sulfates composite) and thermal shock effects.

QMZR-12B, a lower-temperature magnesia-zirconia brick is suited for this area. The other options are QMZ-92, a high density magnesia brick; or QDMC-12, a direct bonded magnesia-chrome brick.

Main Products

Magnesia-Zirconia Brick

Magnesia-Zirconia brick is characterized with high refractoriness, longer service life, and strong creep resistance. It has better corrosion resistance than magnesia-chrome brick, also better than rebonded magnesite brick for C.C.S at high temperature and thermal shock resistance. These brands are used in the top and intermediate zone for regenerator checker.

Magnesite Brick

Sintered brick is batched and fired with different types of heavy or dead-burned magnesia. The higher purity of raw material, the better specification. It is broadly used for regenerator of glass tank.

Fused Magnesite Brick

Fused magnesite brick is made from high-grade-high-purity magnesia together with fused magnesia, characterized with higher density, lower apparent porosity, bigger crystallized periclase, better creep resistance performance. It is broadly applied in the regenerator crown and upper part of wall.

Magnesia-Alumina Brick

Magnesia-alumina brick is made from high quality magnesia and bauxite. It has a better matrix within magnesia alumina spinel, good C.C.S at high temperature, and high thermal shock resistance. It is widely applied in the heat-sensitive zone of regenerator.

Light Forsterite Brick





Mainly using synthetical forsterite clinker as raw material, the Light forsterite brick has good insulation property and superior stability at high temperature. It is widely used in the insulation layer of regenerator wall.

Magnesia-Chrome Brick

With periclase and magnesia-chrome spinel as the main crystal phases, magnesia-chrome brick is made from sintered magnesia and chrome ore, and fired at optimum "sintering curve". They are widely used in regenerator of glass tank.

Mortar

Matched with diversity of bricks, Qinghua develops different range of Mortar, with corresponding grade of magnesia, and suitable binder. These brands have high adhensive strength, easy installating with setting time 120 seconds approximately, and high sintered strength. It performs well as the joint filler for brick lining of regenerator.

Ramming Mix

Ramming mix is made from high quality magnesia with adding a special chemical binder to batches. It is used for joint filling and lining of regenerator. During the hardening process, It forms "chemical-ceramic" change at suitable temperature. 5-7% water shall be added on operation.

Company Profile of Qinghua Refractories Co.,Ltd

A service of glassglobal.com, an affiliate of glassglobal group.

您出版的地址材料版权是属于公司或对它的第三者销售代理,保留所有权。任何用户访问这样的资料的只限于个人使用,并且用户对材料的 用途和使用,风险自担。禁止对其它的贸易广告及地址资料重新发布。这样的地址材料如果是由第三方提供,使用这样的新闻材料必须由各 用户同意和遵守具体使用条款。Glass Global不保证从任何链接或其它网址打印输出的信息的准确性和可靠性。www.glassglobal.com -国 际性的玻璃工业门户 - OGIS GmbH