

This website uses cookies to improve the user's experience during working with our network and to provide users with dedicated services and functions. By further use you agree with that.OKDetails

地址	Xi'an Aofa OptoelectronicsTech. Faraday Rotator/Magneto-Optic Glass No.126, Jin Hua North Road 710032 Xi'an
国家	中国（中华人民共和国）

产品/机械

Faraday Roatator Glass is widely used especially in high-power optical rotator and isolator with large aperture, circulators,switches,polarimeters,magneto-optics sensor,high-power laser systems and other wanted Faraday Effect,etc. The main products as follow,please see Faraday Roatator Glass is widely used especially in high-power optical rotator and isolator with large aperture, circulators,switches,polarimeters,magneto-optics sensor,high-power laser systems and other wanted Faraday Effect,etc.

The main products as follow,please see Product Catalog for details.

* Diamagnetic Faraday Rotator Glass.Type MR1 with very important properties, its high Verdet constant 0.071~0.075min/Oe*cm at 632.8nm,it's independent of temperature from -50°~+135° with better thermal stability and widely used in magneto optical sensor and Magnetic-Optical Current Transducer (MOCT), etc.

* Paramagnetism Faraday Rotator Glass/Magneto-Optical Glasses

Type MR3-2, Verdet constant -0.329 min/Oe-cm at 632.8nm or -95.7 rad/T*m at 632.8 nm

Type MR3, Verdet constant -0.34 min/Oe-cm at 632.8nm or -98.9 rad/T*m at 632.8 nm

Type MR4, Verdet constant -0.38 min/Oe-cm at 632.8nm or -110 rad/T*m at 632.8 nm

MR3 and MR4 are the highest Verdet constant in the market available exclusively from XAOT

* Faraday Rotators Rods with high sensitive and steady which are used for all kinds of magneto optical device and instruments.

Product Description

Faraday Rotator Glass / Magneto Optical Glass

Since glass material in high power laser system is damaged as a consequence of self-focusing,low non-linear refractive index as well as high Verdet constant are important factors for Magneto-Optical Glass

Our world-leading Magneto Optical Glass with very high Verdet factor,we supply them with the shape or size of your choice

Very large plates/disks/rods from diameter 1.00 mm to 300 mm are available

Faraday Rotator Glass / Magnetic Optical Glass mainly used in faraday rotating components,fabricating optics-isolators,faraday rotators,circulators,magneto-optical modulators,optical switchs,interleavers,laser gyroscopes,goniometric devices magneto-optic storage and optical information process system,current measuring transducers for magnetic field measuring and high-voltage transmission line,new generation current sensors,wave guides, iatrolgy,spaceflight control,satellite survey and other functional devices

Faraday Rotator Glass is made with more advanced technologies,so is performance stabilization,sensitive, and inherently immune to interfere.In comparison with artificial crystal,it is inexpensive and easy to get big size block,it has been made into different types of optical fibers,so it's widely used in many fields

Specifications

The Properties of MR3-2 Faraday Rotator Glass / Magneto-Optical Glass

At 20 ° temperature

Verdet Constant -0.329min/Oe*cm or -95.7rad/T*m at 632.8 nm

Verdet Constant -0.108 min/Oe-cm or -31.4 rad/T*m at 1064 nm

Transmission window:400nm-1600nm

Refractive indices

ND=1.7441
Nd=1.7442
NF=1.7544
Nc=1.7400
N1064=1.7178

Optical Quality(Δn) /cm < 1×10^{-6} .

Abbe number:

VD=51.7
Vd=51.0

Nonlinear refractive index n_2 ($\times 10^{-13}$ e.s.u.)=2.74

Figure of merit $V632.8$ (nd/n_2)=0.62

Density (g/cm³):4.92

Transformation temperature T_g : 788°

Sag temperature T_s : 824°

Coeff.of linear thermal expansion:

0 - 300° ($10^{-7}/^\circ$)=62.6

100 - 300° ($10^{-7}/^\circ$)=68.2

Transparence rate $T\% \geq 86\%$ (Uncoated)

Transparence rate $T\% \geq 98\%$ (Coated)

Absorption coefficients < 0.002/cm at 1064nm.

Thermal conductivity=48.10/ °(0-100 °)

dv/dt=0.0016(0-40 °)

dv/dt=0.0006(40-80°)

Bulk laser<

Company Profile of **Xi'an Aofa OptoelectronicsTech.**

A service of glasssglobal.com, an affiliate of glasssglobal group.

您出版的地址材料版权是属于公司或对它的第三者销售代理, 保留所有权。任何用户访问这样的资料的只限于个人使用, 并且用户对材料的用途和使用, 风险自担。禁止对其它的贸易广告及地址资料重新发布。这样的地址材料如果是由第三方提供, 使用这样的新闻材料必须由各用户同意和遵守具体使用条款。Glass Global不保证从任何链接或其它网址打印输出的信息的准确性和可靠性。www.glasssglobal.com - 国际性的玻璃工业门户 - OGIS GmbH